What is claimed is:

1. A mixture comprising
   i) a processing stabilizer selected from the group consisting of hydroxylamine stabilizers, nitrone stabilizers and benzofuran-2-one stabilizers, and
   ii) an antistatic agent selected from the group consisting of an ethoxylated amine and/or an ethoxylated amide.

2. A mixture comprising
   i) a compound of the formula I



(I),

wherein

R_1 is $-(CH_2)_3-\underset{CH_3}{CH}-(CH_2)_3-\underset{CH_3}{CH}-(CH_2)_3-CH-(CH_3)_2$, $-CH_2-CH_2-O-\overset{O}{\overset{\|}{C}}-R_2$,

$-CH_2-CH_2-S-R_3$ or  ,

R_2 is C_7-C_{30}alkyl,

R_3 is C_1-C_{30}alkyl, and

   ii) an antistatic agent selected from the group consisting of an ethoxylated amide and/or a compound of the formula V



(V)

wherein, when m is 1,

R_6 is C_4-C_{24}alkyl, C_4-C_{24}alkenyl or phenyl, and

when m is 2,

R_6 is C_1-C_{24}alkylene, C_4-C_{24}alkenylene or phenylene,

R_7 is hydrogen, C_1-C_{24}alkyl or  ,

R_8  ,

m is 1 or 2, and

n is 1, 2, 3, 4 or 5.

3. A mixture according to claim 1 or 2, comprising in addition, besides components (i) and (ii), further additives selected from the group consisting of phenolic antioxidants, further processing stabilizers, light-stabilizers and acid scavengers.

4. A mixture according to claim 1 or 2, comprising as a further component (iii) a phosphite, a phosphonite or a triarylphosphine.

5. A mixture according to claim 4, wherein component (iii) is tris(2,4-di-tert-butylphenyl)phosphite, bis(2,4-di-tert-butyl-6-methylphenyl)ethyl phosphite, bis(2,4-di-tert-butylphenyl)pentaerythritol diphosphite, bis(2,4-dicumylphenyl)pentaerythritol diphosphite, tris(nonylphenyl) phosphite or tetrakis(2,4-di-tert-butylphenyl)4,4'-biphenylene diphosphonite.

6. A mixture according to claim 1, wherein the hydroxylamine stabilizer as component (i) is a compound of the formula II

 (II)

wherein R_4 and R_5 are each independently of the other C_8-C_{18}alkyl.

7. A mixture according to claim 1, wherein the hydroxylamine stabilizer as component (i) is a N,N-di(alkyl)-hydroxylamine produced by the direct oxidation of N,N-di(hydrogenated tallow)-amine.

8. A mixture according to claim 1, wherein the nitrone stabilizer as component (i) is a compound of the formula III



(III)

wherein

T is C_8-C_{18}alkyl,

G is hydrogen, methyl or ethyl, and

E is C_5-C_{17}alkyl.

9. A mixture according to claim 1, wherein the benzofuran-2-one stabilizer as component (i) is a compound of the formula IV



(IV)

wherein

R_9 is hydrogen or C_1-C_8alkyl,

R_{10} is C_1-C_{12}alkyl,

R_{11} is hydrogen, C_1-C_4alkyl or C_2-C_8alkanoyl,

R_{12} is hydrogen or C_1-C_8alkyl,

R_{13} is hydrogen, C_1-C_4alkyl or C_1-C_4alkoxy, and

R_{14} is hydrogen or C_1-C_{12}alkyl.

10. A mixture according to claim 2, comprising as component (i) a compound of the formula i, wherein R_1 is $-(CH_2)_3-CH(CH_3)-(CH_2)_3-CH(CH_3)-(CH_2)_3-CH(CH_3)_2$.

11. A mixture according to claim 1 or 2, comprising as component (ii) a compound of the formula V



(V)

wherein, when m is 1,

R_6 is C_4-C_{24}alkyl, C_4-C_{24}alkanoyl, C_4-C_{24}alkenyl, C_4-C_{24}alkenoyl, phenyl or benzoyl, and

when m is 2,

R_6 is C_1-C_{24}alkylene, C_4-C_{24}alkenylene or phenylene,

R_7 is hydrogen, C_1-C_{24}alkyl or  ,

R_8  ,

m is 1 or 2, and

n is 1, 2, 3, 4 or 5.

12. A mixture according to claim 11, wherein

R_6 is C_{11}-C_{20}alkyl or C_{11}-C_{20}alkanoyl,

R_7 is hydrogen or  ,

R_8 is  ,

m is 1, and

n is 1 or 2.

13. A mixture according to claim 1, wherein component (i) is N,N-di(alkyl)-hydroxylamine produced by the direct oxidation of N,N-di(hydrogenated tallow)amine, and component (ii) is a C_{13}-C_{18}-alkyl-diethanolamine.

14. A mixture according to claim 2, wherein component (i) a compound of the formula I wherein R_1 is $-(CH_2)_3-\underset{CH_3}{CH}-(CH_2)_3-\underset{CH_3}{CH}-(CH_2)_3-CH-(CH_3)_2$; and component (ii) is a C_{13}-C_{18}-alkyl-diethanolamine.

15. A composition comprising

a) an organic material which is susceptible to oxidative, thermal or light-induced degradation, and

b) a mixture of components (i) and (ii) according to claim 1 or 2.

16. A composition according to claim 15, wherein component (a) is a synthetic polymer.

17. A composition according to claim 15, wherein component (a) is a polyolefin.

18. A composition according to claim 15, wherein component (a) is polyethylene or polypropylene or mixture thereof.

19. A composition according to claim 15, wherein component (b) is present in an amount of from 0.001 to 5 %, based on the weight of component (a).

20. A shaped article containing a mixture according to claim 1 or 2.

21. A process for stabilizing an organic material against oxidative, thermal or light-induced degradation, which comprises incorporating therein or applying thereto at least a mixture according to claim 1 or 2.

22. The use of a mixture according to claim 1 or 2 as stabilizer for organic materials against oxidative, thermal or light-induced degradation.